

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



10/533209



(43) International Publication Date  
13 May 2004 (13.05.2004)

PCT

(10) International Publication Number  
WO 2004/039576 A1

(51) International Patent Classification<sup>7</sup>: B32B 3/10

(21) International Application Number:  
PCT/US2003/033761

(22) International Filing Date: 28 October 2003 (28.10.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
60/421,497 28 October 2002 (28.10.2002) US

(71) Applicant (for all designated States except US):  
GREENER BAGS L.L.C. [US/US]; Suite 202, 303  
East Quincy, San Antonio, TX 78215 (US).

(71) Applicant and

(72) Inventor: SHIH, Chia, Shun [US/US]; 2211 New Oak  
Park, San Antonio, TX 78230 (US).

(74) Agent: SISSON, Thomas, E.; Jackson Walker L.L.P.,  
Suite 2100, 112 E. Pecan Street, San Antonin, TX 78205  
(US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,  
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,  
CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM,  
HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK,  
LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX,  
MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SK, SL, TJ,  
TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,  
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,  
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,  
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declaration under Rule 4.17:

— of inventorship (Rule 4.17(iv)) for US only


Published:

— with international search report

— before the expiration of the time limit for amending the  
claims and to be republished in the event of receipt of  
amendments

For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.

(54) Title: REINFORCED PAPER PRODUCT AND METHOD FOR MAKING SAME



(57) Abstract: A composite paper product has at least inner and outer layers of standard paper bonded to each other and a fiber strand network to form a reinforced paper product. The fiber strand network has a first set of strands extending in a first direction and a second set of strands overlapping the first set and extending in a second direction. In some embodiments the second set of fiber strands overlaps in opposite diagonal directions while overlaying a first set of generally transverse parallel fiber strands. A recyclable binding composition is used to glue the various fiber and paper layers together to yield a unitary sheet of reinforced composite paper.

WO 2004/039576 A1

1 Title: REINFORCED PAPER PRODUCT AND METHOD FOR MAKING SAME

2 Inventor: Chia Shun SHIH

3

4 This utility application claims priority to U.S. Provisional Application Serial  
5 No. 60/421,497, filed October 28, 2002, which is incorporated herein by reference  
6 for all purposes.

7

8 BACKGROUND OF THE INVENTION

9 Over past centuries paper products have been utilized in various packaging,  
10 binding, shipping, storage and building applications in modern life. Currently, most  
11 applications incorporate certain common features, namely, single or multi-layered  
12 paper sheets are cut, pasted, glued or molded into a desired shape or configuration  
13 with various specified dimensions. The tensile strength and abrasive resistance of  
14 current paper products is severely limited by the strength of the underlying paper  
15 composition. Often the paper strength is inadequate for commercial needs such as  
16 shipping, storage, and inter-modal transshipments. Thus, the materials contained or  
17 packaged by current paper products will frequently spill out as the result of paper  
18 failure, or unexpected breakage or rupture. Such failure causes significant loss of  
19 materials and time, workplace contamination and even environmental damage.

20 The present inventive product and method yields an increased tensile strength  
21 and abrasive resistance to the composite product. Depending upon the composition  
22 of the reinforcing fiber selected for inclusion in the composite product, the strength

1 and abrasive resistance may be increased hundreds of fold. Further, the composite  
2 product may be reused significantly reducing overall paper consumption. With  
3 appropriate selection of natural or synthetic fibers, the composite product may be  
4 totally recyclable.

5

6 BRIEF DESCRIPTION OF THE DRAWINGS

7 Fig. 1 is a perspective view of a first embodiment of the composite paper  
8 product of the present invention.

9 Fig. 1A is a detailed view of the fiber strands overlapping.

10 Fig. 2 is a perspective view of a second embodiment of the composite paper  
11 product of the present invention.

12 Fig. 3 is a perspective view of a third embodiment of the present invention.

13 Fig. 4A is a top plan view of a first fiber strand arrangement of the present  
14 invention.

15 Fig. 4B is a top plan view of a second fiber strand arrangement of the present  
16 invention.

17 Fig. 5 is a top plan view of an overlapping of first and second fiber strand  
18 layers of the present invention.

19 Fig. 6 is a perspective view of an embodiment of the present invention  
20 illustrating an insulation composition covering a layer of paper of the present  
21 invention.

Fig. 7 illustrates an abrasive resistant covering of the present invention with a gypsum layer sandwiched therebetween.

Fig. 8 is a flow diagram of the process of the present invention.

#### DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

The reinforced composite paper product of the present invention presents a unique reinforcement of woven natural and synthetic fiber nets glued or bonded between two or more layers of natural, standard paper sheets. Fig. 1 illustrates the simplest configuration of the present inventive composite product 10.

A first paper layer 12 and a second paper layer 14 have a bonded fiber strand network 16 therebetween. Fig. 1A illustrates a detailed view of a pattern of the fiber strand network 16. The fiber network 16 is made up of at least two sets of overlapping fiber strands (each strand is comprised of a multiplicity of individual fiber filaments) which are woven and folded between the paper layers 12 and 14 as described below. The fiber strand network 16 may be made of the following man-made or natural fibers including but not limited to: polyester staple, polyester conjugate, acrylic, viscose staple, glass, nylon, polypropylene, acetate, aramid, asbestos, charvet, elastomerr, glass fibers, latex, manufactured fiber, metallic fibers, modacrylic nylon, olefin fiber, PBI, polyester, protein base fibers, rayon, Spandex® Sulfar®, Vivyon®, polyamide fibers, vinyl, wool and related mammalian fibers, silk, jute and kenaf, other long vegetable fibers, abaca, banana, sisal, henequen, flax, ramie, hemp, sunn, and coir, cotton, cellulose acetate and triacetate fibers.

1           As would be understood by one of ordinary skill in the art, the reinforced  
2 composite product 10 may be used for boxes, bags, molded containers, thermal  
3 insulation, waterproofing, corrosion resistant fire retardant building or packaging  
4 materials, etc. Application of the present inventive fiber reinforced paper product  
5 may result in the following features: waterproofing, tensile strength reinforcement,  
6 thermostability, aging retardation, high anti-abrasion capability, and minimize  
7 breakage or ruptured rate. With selection of an appropriate fiber-net material and a  
8 gluing compound such as the Vinylon® soluble yarn without condensating  
9 aldehydes-treatment, and a PVA based glue, the composite paper product may be  
10 easily dissolved in warm water and become totally recyclable without pollution to  
11 the environment. The paper composite product of the present invention may be  
12 applied to packaging or bagging of all kinds, powdered and particulate materials for  
13 agriculture grains, animal feed, cheese, starch and the floury food products, cement,  
14 fertilizers, pesticides, herbicides, talcum powder, titanium white, carbon black,  
15 calcium carbide, asphalt, and all kinds of chemical and mineral products.

16           Fig. 2 illustrates an exploded perspective view of an embodiment of the  
17 present invention 10a wherein multiple layers of paper 12a, 13a, 13b, and 14a are  
18 separated by multiple layers of fiber strand sets 16a, 16b, 16c, and 16d. Fig. 2  
19 illustrates the strand sets 16a, 16b, 16c, and 16d as if they are woven sheets for  
20 simplicity purposes. However as will be understood below that the warp and woof  
21 (or weft) of the strands are laid down in a weaving process. It is believed that fiber

1 strand network 16 may be woven as separate sheets or nets and placed and glued or  
2 bonded between the paper layers and the layers.

3 It should be noted in Fig. 2 that a plurality of first fiber strands 16a and 16c  
4 extend in a first linear direction and each separate first fiber strand (made up of  
5 multifiber filaments) is generally parallel to the next separate strand. This is a first  
6 direction or orientation for the first fiber strands 16a. A second plurality of fiber  
7 strands 16b and 16d extend in a second diagonal direction and each second fiber  
8 strand is generally parallel to the next strand. As shall be noted below, a third  
9 diagonal direction may be used on a portion of the second strands 16a and 16d which  
10 is opposite the second diagonal direction.

11 In the embodiment of Fig. 2, it will be seen that two paper sheets or layers  
12 13a and 13b may be glued adjacent one another without detracting from the  
13 advantages of the present invention. Either or both of the outermost sheets of paper  
14 12a and 14a may be coated, covered, or treated with a variety of compositions to  
15 integrate special characteristics to the composite product. These compositions may  
16 include a water proofing treatment composition, a corrosion proofing or resistance  
17 treatment composition, a thermal insulation composition, a fire retardation  
18 composition, and an abrasion resistance composition.

19 A binding composition or glue 15 is disposed or deposited between the paper  
20 layers and retains the first fiber strands 16a and 16b and the second fiber strands 16c  
21 and 16d in the directions noted above. The glue 15 also binds or adheres the paper

1 layers together to create a unitary, composite, reinforced fiber paper product or sheet.  
2 As noted below, the glue may be applied first to the warp yarn.

3 Fig. 3 illustrates another embodiment of the present invention wherein a  
4 plurality of paper sheets 12a, 13a, 13b, 13c, and 14a are separated by a plurality of  
5 first fiber strand sets 16a extending in a first direction and a plurality of second fiber  
6 strand sets 16b extending in a second diagonal direction between two adjacent layers  
7 of paper. As noted above, a binding composition such as polyvinyl alcohol (PVA) or  
8 other biodegradable glue 15 is used to hold the layers of paper and fiber together in a  
9 unitary sheet. The fibers themselves may be made of PVA.

10 In Figs. 4A, 4B, and 5, the fiber strand network 16 is shown in greater detail.  
11 Fig. 4A illustrates the first fiber strand pattern 16a which is made up of generally  
12 transverse, parallel rows of fiber filament bundles. Fig. 4B shows a second fiber  
13 strand pattern 16c with a first portion of the strands 20 extending diagonally in a  
14 generally parallel configuration in one direction and a second portion of fiber strands  
15 22 extending diagonally in a generally parallel configuration in an opposite direction.  
16 Fig. 5 illustrates how the two patterns 16a and 16c have been overlain to form the  
17 network 16.

18 Figs. 6 and 7 are illustrative of how the composite product of the present  
19 invention may be combined with insulation material 40 (Fig. 6) or even composite  
20 gypsum board 50 (Fig. 7) to form very functional building materials. In Fig. 6, an  
21 exterior paper layer 30 has been bonded to a fiber strand network 16 and an interior

1 paper layer 32. This forms a very strong construction paper product to which an  
2 insulation material 36 has been bonded.

3 Fig. 7 illustrates a different building product 50 which incorporates two  
4 sheets of the composite reinforced paper product 31 and 33 with a section of gypsum  
5 material sandwiched therebetween. This product 50 has a very high abrasion  
6 resistance and may be used in numerous building applications.

7 As should be understood, the composite paper product of the present  
8 invention may be used to make bags, boxes, containers, tarps, cups and many other  
9 paper products which may be enhanced by its reinforced strength and recyclable  
10 attributes.

11 A preferred process for constructing or manufacturing the present inventive  
12 paper product is illustrated in Fig. 8 and is described as follows:

- 13 1. The multiple lines of warp yarn 100 are rolled off the spindles 101.
- 14 2. All lines of the warp yarn are dipped through the glue bath 102.
- 15 3. At the same time when the warp yarn 100 begins its movements, pre-  
16 sized interior layer of paper 104 is rolled off the paper spool 105 and is pulled under  
17 the warp yarn 100. A portion of the glue is disposed on the paper layer 104.
- 18 4. Preset lines of weft (or woof) yarn 110 are pulled to form a transverse  
19 net and passed above the warp yarn and the interior paper.
- 20 5. The net 16 formed by the yarn and the interior paper are moved by  
21 rollers and warped into a paper tube 112.



1           6.       The printed exterior paper 114 is pulled to wrap around the tube and  
2 moved through the calendar 116 to press into a tube made of composite paper 118  
3 with the fiber net reinforcement.

4           7.       The tube is rolled through a pinhole-punching machine 120.

5           8.       The punched paper tube 122 is then rolled through the margin-folding  
6 machine 124.

7           9.       The folded paper tube 126 is then moved through the bag-cutting  
8 machine 128 based on preset length.

9           10.      The bag 130 is then dropped into a bag bin 132 for further processing.

10          In case a flat composite paper sheet is the final product, the paper tube made  
11 through step number 6 will be diverted to a horizontal cutting machine which can cut  
12 the tube into flat sheet.

13          It should be understood in the current process of Fig. 8 that with the selection  
14 of the yarns made of polyvinyl alcohol (PVA), the composite paper products are  
15 totally recyclable. Normally, PVA is frequently applied in paper making and can be  
16 dissolved easily and the temperature above 200° F. Multiple layers of paper with  
17 the fiber net glued between the paper can easily be produced with the sequential  
18 application of the present inventive production process.

19          Generally, the invented composite paper with the fiber net and the PVA glue  
20 is water resistant in normal conditions. In view of the strength requirements and  
21 preferences of fiber nets made of natural or synthetic material, different fiber nets  
22 can be applied.

1           Although the invention has been described with reference to a specific  
2   embodiment, this description is not meant to be construed in a limiting sense. On the  
3   contrary, various modifications of the disclosed embodiments will become apparent  
4   to those skilled in the art upon reference to the description of the invention. It is  
5   therefore contemplated that the appended claims will cover such modifications,  
6   alternatives, and equivalents that fall within the true spirit and scope of the invention.  
7

1. CLAIMS:

2

3 1. A reinforced composite paper product comprising:  
4 at a first paper layer and at least a second paper layer;  
5 a plurality of first fiber strands extending across said first paper layer in a  
6 first direction;  
7 a plurality of second fiber strands extending across said first fiber strands in a  
8 second direction;  
9 a binding composition disposed between said first paper layer and said  
10 second paper layer, said composition retaining said first fiber strands and said second  
11 fiber strands in said directions and binding said strands between said first and said  
12 second paper layers and further binding said first paper layer to said second paper  
13 layer.

14

15 2. A reinforced composite paper product comprising:  
16 a plurality of paper layers;  
17 a plurality of first fiber strands extending in a first direction between any two  
18 adjacent layers of said plurality of paper layers;  
19 a plurality of second fiber strands extending in a second direction between  
20 said any two adjacent layers of said plurality of paper layers;  
21 a binding composition disposed between said any two adjacent layers of said  
22 plurality of paper layers, said composition retaining said plurality of said first and

1 second fiber strands in said directions and binding said strands between said any two  
2 adjacent paper layers and further binding said any two adjacent paper layers to each  
3 other.

4

5 3. The composite paper product of claim 2 wherein said binding composition is  
6 disposed between said plurality of paper layers binding all of said paper layers and  
7 said fiber strands into a single, multi-layered composite sheet.

8

9 4. The composite paper product of claim 3 wherein said all of said first fiber  
10 strands extend in a same first direction and all of said second fiber strands extend in  
11 a same second direction.

12

13 5. The composite paper product of claim 1 wherein a portion of said plurality of  
14 second fiber strands extend across said first fiber strands in a third direction.

15

16 6. The composite paper product of claim 5 wherein a first portion of said second  
17 fiber strands extends diagonally across said first fiber strands in a first diagonal  
18 direction and a second portion of said second fiber strands extends diagonally across  
19 said first fiber strands in a second opposite diagonal direction.

20

21 7. The composite paper product of claim 1 wherein an outermost first and  
22 second paper layer is covered with a composition selected from the group consisting

1 of a water proofing treatment composition, a corrosion proofing treatment  
2 composition, a thermal insulating composition, a fire retardation composition, and an  
3 abrasion resistance composition.

4

5 8. The composite paper product of claim 2 wherein an outermost one of said  
6 plurality of paper layers is covered with a composition selected from the group  
7 consisting of a water proofing treatment composition, a corrosion proofing treatment  
8 composition, a thermal insulating composition, a fire retardation composition, and an  
9 abrasion resistance composition.

10

11 9. A method of producing a reinforced composite paper product comprising:

12 a. rolling multiple lines of a warp yarn fiber from a multiplicity of warp  
13 spindles;

14 b. passing said warp yarn fibers through a glue bath;

15 c. rolling an interior layer of paper beneath said glue bathed warp yarn  
16 fibers;

17 d. transversely weaving weft yarns over said glue bathed warp yarn  
18 fibers and said interior layer of paper to form a fiber strand network;

19 e. rolling said network in said interior paper layer via rollers to form a  
20 reinforced paper tube;

21 f. wrapping around said reinforced paper tube an exterior layer of paper;

- 1           g.       passing said reinforced paper tube and said exterior layer of paper
- 2    through a calendar to press said tube and exterior layer into said reinforced,
- 3    composite paper product.
- 4




Fig. 1





Fig. 1A

2/6

*Fig. 2*



3/6




Fig. 3

4/6




Fig. 4A




Fig. 4B






Fig. 5

5/6



*Fig. 6*



*Fig. 7*




Fig. 8

# INTERNATIONAL SEARCH REPORT

International application No.

PCT/US03/33761

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : B32B 3/10  
US CL : 428/44,105,113

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
U.S. : 428/44,105,113

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4,820,568 A (HARPELL et al) 11 April 1989 (11.04.1989), see entire document.	All
A	US 4,204,016 A (CHAVANNES) 20 May 1980 (20.05.1980), see entire document.	All

☐ Further documents are listed in the continuation of Box C.

☐ See patent family annex.

* Special categories of cited documents:	
"A" document defining the general state of the art which is not considered to be of particular relevance	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"E" earlier application or patent published on or after the international filing date	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"O" document referring to an oral disclosure, use, exhibition or other means	"&" document member of the same patent family
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

12 March 2004 (12.03.2004)

Date of mailing of the international search report

14 APR 2004

Name and mailing address of the ISA/US

Mail Stop PCT, Attn: ISA/US  
Commissioner for Patents  
P.O. Box 1450  
Alexandria, Virginia 22313-1450

Facsimile No. (703)305-3230

Authorized officer

Nasser Ahmad

Telephone No. 571-272-1487

Jean Proctor  
Paralegal